



# TEST CERTIFICATE

## CERTIFICATO DI COLLAUDO

Type / Tipo 2.2 Reference / Riferimento UNI EN 10204:2005

| Sample Result Name | Type         | Measure Date Time       | Recalculation Date Time | Origin                        | Method Name | Method Version    | Operator Name | Correction Type         | Type Corr Sample Name |
|--------------------|--------------|-------------------------|-------------------------|-------------------------------|-------------|-------------------|---------------|-------------------------|-----------------------|
|                    |              | 9/26/2016 2:43:41 PM    | 9/26/2016 2:43:41 PM    | Measured                      | Cu-50MO     |                   |               | None                    |                       |
| Check Type         | Check Status | Grade Verification Name |                         | Grade Verification Similarity |             | Grade Search Name |               | Grade Search Similarity |                       |
|                    |              | CB491K                  |                         |                               |             |                   |               |                         |                       |
| FORNITORE          | NR. BOLLA    | ARTICOLO                | LEGA                    | RIF.NORMA                     | CLIENTE     | DATA BASE         | NOTE          |                         |                       |
|                    |              |                         | CB491K                  |                               |             | MAESTRINI         |               |                         |                       |

**Elements Conc.**

| Meas.         | Zn    | Pb    | Sn    | P      | Mn      | Fe    | Ni    | Si      | Cr       | As    |
|---------------|-------|-------|-------|--------|---------|-------|-------|---------|----------|-------|
|               | %     | %     | %     | %      | %       | %     | %     | %       | %        | %     |
|               | Conc. | Conc. | Conc. | Conc.  | Conc.   | Conc. | Conc. | Conc.   | Conc.    | Conc. |
| <b>W. Min</b> | 4.00  | 4.00  | 4.00  |        |         |       |       |         |          |       |
| <b>Mean</b>   | 5.03  | 4.16  | 4.32  | <0.002 | <-0.001 | 0.10  | 0.57  | <-0.001 | <-0.0004 | 0.008 |
| <b>W. Max</b> | 6.00  | 6.00  | 6.00  |        | 0.100   | 0.30  | 0.60  |         |          |       |

| Meas.         | Sb    | Bi      | Ag    | Al      | S     | Cu    |  |  |  |
|---------------|-------|---------|-------|---------|-------|-------|--|--|--|
|               | %     | %       | %     | %       | %     | %     |  |  |  |
|               | Conc. | Conc.   | Conc. | Conc.   | Conc. | Conc. |  |  |  |
| <b>Mean</b>   | 0.046 | <-0.048 | 0.017 | <-0.004 | 0.021 | 85.8  |  |  |  |
| <b>W. Max</b> | 0.30  |         |       |         | 0.100 |       |  |  |  |